

Nominal spec.	250	300	400	500	+/- 10%	Tolerance %
Thickness- micron	250	300	400	500	+/- 10%	(-0% 400mic)
Roll length mts	25	25	20	12.5	-0/ + 5%	
Roll width mts	4	4	4	4	-0/5%	
Colours- blue/ black/ yellow/clear.						

TEST. EN13967.

	250MU	300MU	400MU	500MU
TENSILE-EN12311:2	100MLV	125MLV	180MLV	240MLV
THICKNESS -EN1849-2	+/- 10%	+/- 10%	-0/+10%	+/-10%
DROP DART-EN12691	30MLV	30MLV	30MLV	30MLV
WIDTH – EN1848-2	4MT	4MT	4MT	4MT
NAIL TARE-EN12310	120MLV	130MLV	180MLV	200MLV

BBA TESTING.

STATIC LOAD EN 12730

ALL PASS @ 20KGS METHOD B.

WATER PERMEABILITY-EN1931 PASS

WATER TIGHTNESS-EN1928

*CONTROL- PASS

*CHEMICAL - PASS

*HEAT AGED- PASS



Signed for and on behalf of manufacturer
**Douglas Mercer, Managing Director, Frank Mercer &
Sons Ltd**

Accredited

Reprocessor
DOE ER199846

Signed

Date

Valpak

2001 Challenge
Award Winner
Recycling

Chequerbent Works
Tel: 01942 841111

• Manchester Road
• Fax: 01942 842388

• Westhoughton
• sales@toughsheet.com

• Bolton BL5 3JF

• www.toughsheet.com